

# Welding Connections to Pipe

API RECOMMENDED PRACTICE 5C6  
SECOND EDITION, MARCH 2006





# Welding Connections to Pipe

## Upstream Segment

API RECOMMENDED PRACTICE 5C6  
SECOND EDITION, MARCH 2006



## SPECIAL NOTES

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, N.W., Washington, D.C. 20005.

Copyright © 2006 American Petroleum Institute

## FOREWORD

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, N.W., Washington, D.C. 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, N.W., Washington, D.C. 20005.

Suggested revisions are invited and should be submitted to the Standards and Publications Department, API, 1220 L Street, NW, Washington, DC 20005, [standards@api.org](mailto:standards@api.org).

This 2nd edition of RP 5C6 contains only editorial changes from the previous edition. SR 21 through 25 were already in use in other standards.

The following is a list of changes included in this edition.

Page vi: change SR 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31 to  
SR 26, 27, 28, 29, 30, 31, 32, 33, 34, 35, 36 respectively

5.5; change SR 23 and 24 to SR 27 and 28 respectively

5.6.3; change SR 30 to SR 35

7.4; change SR 29 to SR 34

8.2.2; change SR 29 to SR 34

8.2.4; change SR 29 to SR 34

A.1; change SR 21 to SR 26

A.2; change SR 22 to SR 27

A.2 change Section 4.5 to Section 5.5

A.3; change SR 23 to SR 28

A.3; change Section 4.5 to Section 5.5

A.4; change SR 24 to SR 29

A.5; change SR 25 to SR 30

A.6; change SR 26 to SR 31

A.7; change SR 27 to SR 32

A.8; change SR 28 to SR 33

A.9; change SR 29 to SR 34

A.9; change Section 7.2.2 to section 8.2

A.10; change SR 30 to SR 35

A.11; change SR 31 to SR 36

Copyright American Petroleum Institute  
Provided by IHS under license with API  
No reproduction or networking permitted without license from IHS

# CONTENTS

	Page
1 SCOPE.....	1
1.1 Purpose.....	1
1.2 Equipment .....	1
1.3 Supplemental Requirements .....	1
2 REFERENCED STANDARDS .....	1
3 DEFINITIONS AND ABBREVIATIONS.....	2
4 MATERIALS INFORMATION REQUIREMENTS .....	3
4.1 Documentation.....	3
4.2 Pipe.....	3
4.3 Connectors .....	3
5 WELDING PROCEDURE QUALIFICATION.....	4
5.1 Written Procedure .....	4
5.2 Base Metal Groupings .....	4
5.3 Welding Consumables .....	4
5.4 Hardness Testing .....	4
5.5 Charpy Impact Testing.....	5
5.6 Postweld Heat Treatment (PWHT) .....	5
6 WELDER AND WELDING OPERATOR QUALIFICATION .....	5
6.1 Testing Requirements .....	5
6.2 Records.....	5
7 PRODUCTION WELDING CONTROLS.....	5
7.1 Qualifications.....	5
7.2 Use of WPS .....	5
7.3 Preheating.....	5
7.4 Fit-up .....	5
7.5 Postweld Heat Treatment.....	6
7.6 Welding Controls .....	6
8 INSPECTION .....	6
8.1 Calibration of Measuring and Test Equipment .....	6
8.2 Connector Squareness and Alignment Verification .....	6
8.3 Nondestructive Examination of Weldments .....	6
APPENDIX A SUPPLEMENTARY REQUIREMENTS .....	9
Figures	
1 Connector Dimensional Considerations .....	vii
A-1 Rockwell Method .....	9
A-2 Vickers Method.....	9

## SUGGESTIONS FOR ORDERING EQUIPMENT

In placing orders for connectors to be welded to pipe in accordance with this recommended practice, the purchaser should specify the following in the purchase order:


Checklist	Requirement
<input type="checkbox"/>	Specification
<input type="checkbox"/>	Quantity
<input type="checkbox"/>	Delivery date
<input type="checkbox"/>	Shipping instructions
<b>Type of Pipe</b>	
<input type="checkbox"/>	Specification (include edition & grade)
<input type="checkbox"/>	Diameter
<input type="checkbox"/>	Weight per foot or wall thickness
<input type="checkbox"/>	Range
<b>Type of Connector</b>	
<input type="checkbox"/>	Manufacturer's designation
<input type="checkbox"/>	Connector dimensional considerations (see Figure 1)
<input type="checkbox"/>	Description of welded attachments (pad eyes, lift eyes, etc.)
<input type="checkbox"/>	Radiographic examination per API Spec 1104 is standard

Supplemental requirements are listed below. As supplements, these are nonstandard but occasionally imposed and identified on the purchase order prior to production work.

SR 26	Hardness testing for the welding procedure qualification record (PQR)
SR 27 or SR 28	Impact testing for the PQR
SR 29	Radiographic examination per ASME Code, Section VIII
SR 30	Magnetic particle examination per ASME Code, Section V and VIII
SR 31	Production hardness testing
SR 32	Full length drift testing
SR 33	End drift testing
SR 34	Connector to connector alignment
SR 35	Compliance to NACE MR0175
SR 36	Ultrasonic examination



## Suggestions for Ordering Equipment (Continued)



When selecting connectors for an application, care should be taken to assess the geometry of the connector. The connector I.D. shall be large enough to allow passage of any hardware that will subsequently run through the connector. The connector O.D. shall be smaller than the openings through which it will be run.

Connector type shown is threaded. The same consideration shall be given to mechanical connectors as well.

Figure 1—Connector Dimensional Considerations



# Welding Connections to Pipe

## 1 Scope

### 1.1 PURPOSE

This recommended practice was created to provide a standard industry practice for the shop or field welding of connectors to pipe.

The technical content provides requirements for welding procedure qualification, welder performance qualification, materials, testing, production welding and inspection. Additionally, suggestions for ordering are included.

### 1.2 EQUIPMENT

This recommended practice covers the weld fabrication of connectors and handling attachments such as lift eyes and landing pads to pipe.

This document includes practices currently being implemented by a broad spectrum of the industry. This recommended practice is intended to be analogous to API 6A PSL 1 with additional requirements specific to the equipment fabrication.

### 1.3 SUPPLEMENTAL REQUIREMENTS

Supplements to this recommended practice shall not be considered as requirements except when specified on the purchase order.

## 2 Referenced Standards

Unless otherwise specified, the most recent editions or revisions of the following standards, codes, and specifications shall, to the extent herein, form a part of this standard.

#### API

Spec 6A	<i>Specification for Wellhead and Christmas Tree Equipment</i>
Spec 1104	<i>Welding of Pipelines and Related Facilities</i>
Spec 5L	<i>Specification for Line Pipe</i>
Spec 5CT	<i>Specification for Casing and Tubing</i>

#### ASME<sup>1</sup>

*Boiler and Pressure Vessel Code, Section IX, Section V, and Section VIII, Division I*

#### AWS<sup>2</sup>

D1.1	<i>Structural Welding Code – Steel</i>
------	--

#### ASTM<sup>3</sup>

A370-92	<i>Standard Methods and Definitions for Mechanical Testing of Steel Products</i>
E10	<i>Brinell Hardness of Metallic Materials</i>
E18	<i>Standard Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic materials</i>
E140	<i>Standard Hardness Conversion Tables for Metals</i>

#### NACE<sup>4</sup>

MR0175	<i>Sulfide Stress Cracking Resistant Metallic Materials for Oilfield Equipment</i>
--------	--

<sup>1</sup>American Society for Mechanical Engineers, 345 East 47th Street, New York, New York 10017, [www.asme.org](http://www.asme.org).

<sup>2</sup>American Welding Society, 550 N.W. Le Jeune Road, Miami, Florida, 33135, [www.aws.org](http://www.aws.org).

<sup>3</sup>American Society for Testing and Materials, 100 Bar Harbor Drive, West Conshohocken, Pennsylvania 19428, [www.astm.org](http://www.astm.org).

<sup>4</sup>NACE International (formerly the National Association of Corrosion Engineers), P.O. Box 218340, Houston, Texas 77218-8340, [www.nace.org](http://www.nace.org)

### 3 Definitions and Abbreviations

**3.1 alignment:** Refer to Section 8 of this document.

**3.2 API:** American Petroleum Institute.

**3.3 ASME:** American Society for Mechanical Engineers.

**3.4 ASTM:** American Society for Testing and Materials.

**3.5 AWS:** American Welding Society.

**3.6 axial alignment:** Alignment to within specified tolerances of the connector centerline, to the centerline of the connector at the opposite end of the pipe.

**3.7 base metal:** Metal to be welded or cut

**3.8 base metal grouping:** System used to describe comparable base metal characteristics such as chemical composition, weldability, thermal processing, and mechanical properties.

**3.9 calibration:** Comparison and adjustment of instruments to a standard of known accuracy.

**3.10 carbon equivalent:** Equation where variables are defined by base metal composition. The result is used as information to help assess the base metal weldability.

**3.11 casing:** Steel pipe used in oil wells to seal off fluids from the bore and to prevent the walls of the hole from sloughing off or caving.

**3.12 connector:** Forging, machined to a geometry to function as a mechanical connection welded to pipe or casing. Other materials may be used if approved by purchaser.

**3.13 connector parallelism:** A measure of the connector face or plane with respect to the connector face at the opposite end of the pipe.

**3.14 CVN impact test:** Charpy V-notch impact testing in accordance with ASTM A370.

**3.15 discontinuity:** An interruption of the typical structure of a weldment such as lack of homogeneity in the mechanical, metallurgical, or physical characteristics. A discontinuity is not necessarily a defect.

**3.16 drift mandrel:** A precision dimensioned cylinder sized to pass through or be inserted into the ends of pipe. It is passed through or into the pipe end ID to locate obstructions or to assure compliance with appropriate specifications. Other drift configurations shall be approved by purchaser.

**3.17 fabricator:** The company responsible for welding.

**3.18 grinding:** Removing material from a pipe surface or weld by abrading, e.g., grinding wheel.

**3.19 hardness test:** A measure of the hardness of a metal, as determined by pressing a hard steel ball or diamond penetrant into a smooth surface under standard conditions. Results are often expressed in terms of Rockwell hardness number (HRB or HRC) or Brinell Hardness Number (BHN). Refer to the latest editions of ASTM E10 and ASTM E18 for added information.

**3.20 heat affected zone (HAZ):** Base metal zone adjacent to a weld that has had a metallurgical change induced by welding.

**3.21 manufacturer:** The company that manufactures the connector.

**3.22 magnetic particle examination:** A nondestructive test method utilizing magnetic flux leakage fields and suitable indicating materials to disclose surface and near-surface discontinuity indications.

**3.23 NACE:** National Association of Corrosion Engineers, previously NACE, now NACE International, Inc.

**3.24 nondestructive exam (NDE):** Inspection to detect internal, surface, and concealed defects or flaws in materials using techniques that do not damage or destroy the items being tested.

**3.25 pipe:** In this document refers to plain end pipe to which connectors are to be welded.

**3.26 postweld heat treat (PWHT):** Thermal heat treatment applied at the completion of a weld as specified on the welding procedure specification.



**3.27 radiographic examination:** The use of x-rays or nuclear radiation, or both, to detect discontinuities in material and to present their images on a recording medium.

**3.28 squareness:** A measurement of the connector with respect to the pipe axis adjacent to the pipe end.

**3.29 weld:** A localized coalescence of metals produced either by heating the materials to the welding temperature, with or without the application of pressure and with or without the use of filler metal.

**3.30 weld reinforcement:** Weld metal in excess of the quantity required to fill a joint sometimes referred to as the weld cap on the O.D. and weld protrusion on the I.D.

**3.31 welded attachments:** Attachments are equipment such as lift wyes and handling pads described on the purchase order to supplement standard design of connector to pipe.

**3.32 welding consumables:** Materials added to the coalescence of base metal (weld) that directly affect the weld metal's properties.

**3.33 welding procedure qualification record (PQR):** A record of the welding data used to weld a test coupon. The PQR is a record of variables recorded during the welding of the test coupons.

**3.34 welding procedure specification (WPS):** A written qualified welding procedure prepared to provide direction for making production welds.

**3.35 visual examination:** The primary evaluation of the fabrication weld joint. Visual aids and gauges are sometimes used. Inspection of welds usually includes quantitative as well as quality assessment of the joint.

**3.36 welder performance qualification (WPQ):** The qualification of a welder or welding operator. The qualification requires the welder or welding operator to weld a test coupon in accordance with the WPS. The test coupon is then tested in accordance with the applicable welding code. The qualification limitations are provided in the requirements of the applicable welding code.

## 4 Materials Information Requirements

### 4.1 DOCUMENTATION

When materials (pipe or connectors) are furnished by the purchaser, they should be accompanied by traceable material test reports or data sheets stating chemical analysis, heat treatment condition and mechanical properties to allow for selection of welding procedure specifications by the fabricator.

### 4.2 PIPE

**4.2.1** Pipe may be supplied by the fabricator or the purchaser, as specified in the purchase order.

**4.2.2** Pipe may be any of the following as specified in the purchase order:

- a. Pipe manufactured in accordance with API Specification 5L.
- b. Pipe manufactured in accordance with API Specification 5CT.
- c. Pipe manufactured in accordance with other industry, national, or international standards (e.g., ASTM, BS, ISO) or with modifications to specifications or standards, as specified in the purchase order.

**4.2.3** For API Specification 5L grades with specified minimum yield strength of 60 ksi and higher, the following additional information regarding pipe manufacturing shall be provided:

- a. Process of manufacture (e.g., controlled rolling).
- b. Specific processing temperature ranges, if applicable.
- c. Specific heat treatment temperatures, if applicable.

### 4.3 CONNECTORS

**4.3.1** Connectors may be supplied by the fabricator or the purchaser, as specified in the purchase order.

**4.3.2** Forgings for connectors may be carbon steel, low alloy steel, microalloyed steel, or other types of weldable materials based on the design requirements for strength, toughness, and other considerations. Materials other than forgings may be used with purchaser approval.

## 5 Welding Procedure Qualification

### 5.1 WRITTEN PROCEDURE

**5.1.1** Welding procedure specifications (WPS) shall be written and qualified in accordance with Article II of the ASME Code Section IX, and as described in this recommended practice.

**5.1.2** The WPS shall identify essential, nonessential, and (when required) supplementary essential variables specified by the ASME Code, Section IX for each welding process and materials to be welded.

**5.1.3** The welding procedure qualification records (PQR) shall record all essential and (when required) supplementary essential variables associated with the qualification tests.

**5.1.4** Both WPS and PQR documents shall be maintained a minimum of 5 years.

### 5.2 BASE METAL GROUPINGS

**5.2.1** ASME Code, Section IX lists base metal groupings. However, as a minimum, base metal groupings shall be based on material strength to ensure that weld joint strength meets the design requirements.

**5.2.2** Additionally, the base metal groupings shall be based on one or more of the following technical considerations:

a. Carbon equivalency formula, where:

$$CE = C + \frac{Mn + Si}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$

or

$$CE = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$

b. Composition parameter Pcm, where:

$$Pcm = C + \frac{Si}{30} + \frac{Mn}{20} + \frac{Cu}{20} + \frac{Ni}{60} + \frac{Cr}{20} + \frac{Mo}{15} + \frac{V}{10} + 5B$$

c. Material heat treatment condition.

### 5.3 WELDING CONSUMABLES

**5.3.1** The WPS shall identify the filler metal AWS classifications that can be used with the procedure.

**5.3.2** If no AWS classification applies to the consumable, the commercial designation or brand name of the consumable shall be documented as part of the PQR used to qualify the procedure.

**5.3.3** Consumables not within the AWS classification system shall be specified on the WPS and become an essential variable for that procedure.

### 5.4 HARDNESS TESTING

When compliance of the welding procedure to NACE MR0175 is specified by a supplementary requirement, the fabricator shall perform hardness testing and record as part of the PQR in order to determine the maximum hardness of the weldment.

Testing shall be performed in accordance with ASTM E18 for the Rockwell method and shall include, as a minimum, surveys of the weld metal and the base material heat affected zones (HAZ).

When other hardness methods have been performed, results may be converted to Rockwell, as applicable, in accordance with ASTM E140. Brinell hardness survey is not acceptable for testing weld metal heat affected zone in a PQR test.

## **5.5 CHARPY IMPACT TESTING**

When impact testing is specified by a supplementary requirement, it shall be performed in accordance with ASTM A370 using the Charpy V-Notch specimen.

A minimum of one set of three test specimens shall be removed at the  $\frac{1}{4}$  thickness location of the test weldment for the weld metal, connector HAZ, and pipe HAZ, unless otherwise specified.

The root of the notch shall be oriented normal to the surface of the test weldment. The weld metal specimens shall have the notched portion composed of 100 percent weld metal. The base material HAZ specimens shall have the notched portion sampling as much HAZ material as possible.

Results of testing shall comply to the applicable specified supplementary requirement. Refer to Supplements SR 27 and SR 28.

## **5.6 POSTWELD HEAT TREATMENT (PWHT)**

**5.6.1** If PWHT is specified by the WPS, all PQR testing shall be done with the test weldment in the postweld heat treatment condition. PWHT shall be performed in accordance with the fabricator's WPS or the written procedure. Both furnace and local resistance type PWHT methods shall be considered acceptable. Heating by direct flame impingement shall not be permitted.

**5.6.2** The PWHT procedure or WPS shall specify the applicable PWHT temperature range and time at temperature.

**5.6.3** When SR 35 is specified on the purchase order, PWHT shall be in compliance with NACE MR0175.

# **6 Welder and Welding Operator Qualification**

## **6.1 TESTING REQUIREMENTS**

Welders and welding operators shall be qualified in accordance with Article III of the ASME Code, Section IX.

## **6.2 RECORDS**

Records of welding performance qualification (WPQ) shall include all essential welding variables and qualified ranges, as specified in ASME Code, Section IX.

# **7 Production Welding Controls**

## **7.1 QUALIFICATIONS**

Welding shall be in accordance with qualified WPS and should be performed by qualified welders or welding operators.

## **7.2 USE OF WPS**

Welders and welding operators shall have access to and should comply with the welding parameters specified in the WPS.

## **7.3 PREHEATING**

Preheating, when required, shall be performed in accordance with the WPS or other written procedures or specifications.

## **7.4 FIT-UP**

The weld joint fit-up shall take into account squareness. The fabricator shall develop a procedure for fit-up methods. SR 34 of this document provides an optional alignment procedure suitable to meet the intent of this recommended practice.



## 7.5 POSTWELD HEAT TREATMENT

When required, PWHT shall be in accordance with the applicable qualified WPS or written procedure.

## 7.6 WELDING CONTROLS

**7.6.1** The fabricator's welding control system shall include procedures for monitoring, updating, and controlling the qualification of welders or welding operators and the use of WPS.

**7.6.2** Instruments to verify temperature, voltage, and amperage shall be serviced and calibrated in accordance with written procedures or specifications. Temperature indicating crayons may be used to monitor preheat and interpass temperature.

## 8 Inspection

### 8.1 CALIBRATION OF MEASURING AND TEST EQUIPMENT

Equipment used to inspect, test or examine material or other equipment shall be identified, controlled, calibrated, and adjusted at specified intervals in accordance with documented manufacturer instructions, and consistent with referenced industry standards, to maintain the accuracy required by this specification.

### 8.2 CONNECTOR SQUARENESS AND ALIGNMENT VERIFICATION

Squareness of each connector welded to pipe shall be inspected to verify conformance with the following requirements.

#### 8.2.1 Squareness Verification

Squareness is a measurement of the connector with respect to the pipe axis and shall be inspected to assure compliance with the requirements set forth in this recommended practice.

- a. The maximum allowable deviation from square shall be  $\frac{1}{16}$  inch per 12 inches.
- b. All squareness measurements utilizing the pipe O.D. as a reference surface shall be taken at a distance of no less than 2 inches away from the weld.
- c. Squareness verification measurements shall be taken at 2 locations as a minimum at 90 degrees apart.

#### 8.2.2 Alignment Verification

When alignment verification is specified as a supplementary requirement (SR 34), the fabricator shall perform alignment verification as specified below.

Connector to pipe alignment verification is a measurement of one connector face relative to the connector face on the opposite end of the pipe. The measurement includes axial alignment and connector parallelism.

#### 8.2.3 Equipment

Typical alignment verification equipment consists of a set of two fixtures including a target and a telescope (or other sighting or image projection device). These fixtures are positioned on opposite ends of the joint being verified such that they are both parallel with the connector or pipe face and centered with the axial centerline of the connector or pipe end. The target typically consists of a well defined center area (bull's eye) with concentric target circles of a known diameter. The sighting device should be of sufficient magnification to observe sight placement within the prescribed target circle for the length of joint being fabricated (usually 40 feet).

#### 8.2.4 Alignment method

With alignment fixtures made up to the connectors (or pipe end), the connectors should be manipulated and tack welded to satisfy the alignment acceptance criteria specified in SR 34.

### 8.3 NONDESTRUCTIVE EXAMINATION OF WELDMENTS

Conduct visual examination in accordance with API Standard 1104 with the following additional requirements.



### 8.3.1 Weld Reinforcement

Visual inspection shall be conducted to verify compliance with the following restrictions to both the internal and external weld reinforcements. At no point shall the crown of the weld be below the surface of the pipe nor shall it be raised above the parent metal by more than 1/16 inch. Those welds where the raised height of the weld reinforcement exceeds the limits set forth may be brought to within tolerance by grinding.

Weld reinforcement may exceed 1/16 inch when welding reduced bore connectors, girth weld on end opposite the elevator lift end, and other special cases. The fabricator and purchaser may need to consider drift and handling equipment requirements to ensure compatibility.

### 8.3.2 Radiographic Examination

Radiographic examinations shall be conducted in accordance with the procedures set forth in API Standard 1104, Sections 8.1.1 through 8.1.13. All discontinuities located by radiographic examination shall be subject to the acceptance standards presented in Section 6 of API Standard 1104.

### 8.3.3 Production Weld Test Frequency

Nondestructive testing consisting of radiographic and visual inspection shall be conducted on 100 percent of all production welds.



## APPENDIX A—SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements are applicable only when specified on the purchase order.

### A.1 SR 26—Hardness Testing

For the purpose of welding procedure qualification testing, hardness tests across the weld and base material heat affected zone (HAZ) cross section shall be performed and recorded as part of the PQR. Hardness testing locations and frequency shall be by the Rockwell method of the Vickers 10Kg method.

#### A.1.1 ROCKWELL METHOD



Rockwell testing location shall be as shown in Figure A-1. Additionally,

- For a weld cross section thickness less than  $\frac{1}{2}$  inch, four hardness tests each shall be made in the base materials, the weld, and the HAZ.
- For a weld cross section thickness equal to or greater than  $\frac{1}{2}$  inch, six hardness tests each shall be made in the base materials, the weld, and the HAZ.
- For all thicknesses, HAZ hardness tests shall be performed in the base material with  $\frac{1}{16}$  inch of the weld interface and at least one each within  $\frac{1}{8}$  inch from top and bottom of the weld.

#### A.1.2 VICKERS METHOD

Vickers testing locations shall be as shown in Figure A-2. Additionally,

- For a weld cross section thickness less than  $\frac{1}{2}$  inch, four hardness tests each shall be made in the base materials and the weld.
- For a weld cross section thickness equal to or greater than  $\frac{1}{2}$  inch, six hardness tests each shall be made in the base materials and the weld.



## **A.2 SR 27—Impact Testing**

Impact testing shall be performed in accordance with section 5.5 of this recommended practice using Charpy V-notch specimens. Results of testing in the weld and base material HAZ shall meet  $15/10$  ft-lbs (avg ÷ min) at 0°F.

## **A.3 SR28—Impact Testing**

Impact testing shall be performed in accordance with section 5.5 of this recommended practice using the Charpy V-notch technique. Results of testing in the weld and base material HAZ shall meet  $15/10$  ft-lbs (avg ÷ min) at -20°F.

## **A.4 SR29—Radiographic Examination**

Radiographic examination shall be performed in accordance with SAME Code, Section VIII, Division 1 UW-51.

## **A.5 SR30—Magnetic Particle Examination (MPI)**

MPI shall be performed in accordance with ASME Code, Section V, Article 7. Acceptance criteria per ASME Code, Section VIII, Appendix 9, Article 9-1, Paragraph 9-130. Welds subject to MPI shall be identified on the purchase order.

## **A.6 SR31—Production Hardness Testing**

The hardness testing method and acceptance criteria shall be agreed between the fabricator and purchaser. In the event the purchaser has not specified hardness testing method and acceptance criteria on the purchase order, the fabricator's standard method may be used.

The hardness test shall be performed once on each weldment at the following locations:

- a. Connector HAZ.
- b. Weld metal.
- c. Pipe HAZ.

## **A.7 SR32—Full Length Drift**

Each welded joint shall be drift tested throughout the entire length. All drift testing shall be performed with a drift mandrel that is a minimum of 12 inches long. The connector manufacturer shall establish drift diameter and tolerances unless otherwise stated on purchase order.

## **A.8 SR 33—End Drift**

Each welded joint shall be drift tested, passing the drift beyond the connector weld yet not the full length of the pipe. All drift testing shall be performed with a drift mandrel that is a minimum of 12 inches long. The connector manufacturer shall establish the drift diameter and tolerances unless otherwise stated on the purchase order.

## **A.9 SR 34—Connector Alignment**

Connectors on each welded joint shall be aligned and verified per section 8.2 of this recommended practice. The acceptance criteria for connector alignment shall be agreed upon by fabricator and purchaser. Acceptance criteria should, as a minimum, consider connector manufacturer recommendations, connector make-up features and service application.

## **A.10 SR 35—NACE**

Welding shall comply with the requirements of MR0175.

## **A.11 SR 36—Ultrasonic Examination**

Ultrasonic examination shall be performed in accordance with the requirements specified on the purchase order.





American Petroleum Institute

# 2006 Publications Order Form

Effective January 1, 2006.

**API Members receive a 30% discount where applicable.**

The member discount does not apply to purchases made for the purpose of resale or for incorporation into commercial products, training courses, workshops, or other commercial enterprises.

**Available through Global Engineering Documents:**

**Phone Orders:** 1-800-854-7179 (Toll-free in the U.S. and Canada)  
303-397-7956 (Local and International)

**Fax Orders:** 303-397-2740

**Online Orders:** www.global.ihs.com

**Date:** \_\_\_\_\_

☐ **API Member** (Check if Yes)

**Invoice To** (☐ Check here if same as "Ship To")

**Name:** \_\_\_\_\_

**Title:** \_\_\_\_\_

**Company:** \_\_\_\_\_

**Department:** \_\_\_\_\_

**Address:** \_\_\_\_\_

**City:** \_\_\_\_\_ **State/Province:** \_\_\_\_\_

**Zip/Postal Code:** \_\_\_\_\_ **Country:** \_\_\_\_\_

**Telephone:** \_\_\_\_\_

**Fax:** \_\_\_\_\_

**E-Mail:** \_\_\_\_\_

**Ship To** (UPS will not deliver to a P.O. Box)

**Name:** \_\_\_\_\_

**Title:** \_\_\_\_\_

**Company:** \_\_\_\_\_

**Department:** \_\_\_\_\_

**Address:** \_\_\_\_\_

**City:** \_\_\_\_\_ **State/Province:** \_\_\_\_\_

**Zip/Postal Code:** \_\_\_\_\_ **Country:** \_\_\_\_\_

**Telephone:** \_\_\_\_\_

**Fax:** \_\_\_\_\_

**E-Mail:** \_\_\_\_\_

Quantity	Product Number	Title	SO★	Unit Price	Total
	GX5CT08	Spec 5CT, Specification for Casing and Tubing, Petroleum and natural gas industries—Steel pipes for use as casing or tubing for wells		\$168.00	
	G05L43	Spec 5L, Specification for Line Pipe		\$194.00	

☐ **Payment Enclosed** ☐ **P.O. No.** (Enclose Copy) \_\_\_\_\_

☐ **Charge My Global Account No.** \_\_\_\_\_

☐ **VISA** ☐ **MasterCard** ☐ **American Express** ☐ **Diners Club** ☐ **Discover**

**Credit Card No.:** \_\_\_\_\_

**Print Name (As It Appears on Card):** \_\_\_\_\_

**Expiration Date:** \_\_\_\_\_

**Signature:** \_\_\_\_\_

**Subtotal** \_\_\_\_\_

**Applicable Sales Tax (see below)** \_\_\_\_\_

**Rush Shipping Fee (see below)** \_\_\_\_\_

**Shipping and Handling (see below)** \_\_\_\_\_

**Total (in U.S. Dollars)**

★ **To be placed on Standing Order for future editions of this publication, place a check mark in the SO column and sign here:**

*Pricing and availability subject to change without notice.*

**Mail Orders** – Payment by check or money order in U.S. dollars is required except for established accounts. State and local taxes, \$10 processing fee\*, and 5% shipping must be added. Send mail orders to: **API Publications, Global Engineering Documents, 15 Inverness Way East, M/S C303B, Englewood, CO 80112-5776, USA.**

**Purchase Orders** – Purchase orders are accepted from established accounts. Invoice will include actual freight cost, a \$10 processing fee\*, plus state and local taxes.

**Telephone Orders** – If ordering by telephone, a \$10 processing fee\* and actual freight costs will be added to the order.

**Sales Tax** – All U.S. purchases must include applicable state and local sales tax. Customers claiming tax-exempt status must provide Global with a copy of their exemption certificate. **Shipping (U.S. Orders)** – Orders shipped within the U.S. are sent via traceable means. Most orders are shipped the same day. Subscription updates are sent by First-Class Mail. Other options, including next-day service, air service, and fax transmission are available at additional cost. Call 1-800-854-7179 for more information.

**Shipping (International Orders)** – Standard international shipping is by air express courier service. Subscription updates are sent by World Mail. Normal delivery is 3-4 days from shipping date.

**Rush Shipping Fee** – Next Day Delivery orders charge is \$20 in addition to the carrier charges. Next Day Delivery orders must be placed by 2:00 p.m. MST to ensure overnight delivery.

**Returns** – All returns must be pre-approved by calling Global's Customer Service Department at 1-800-624-3974 for information and assistance. There may be a 15% restocking fee. Special order items, electronic documents, and age-dated materials are non-returnable.

**\*Minimum Order** – There is a \$50 minimum for all orders containing hardcopy documents. The \$50 minimum applies to the order subtotal including the \$10 processing fee, excluding any applicable taxes and freight charges. If the total cost of the documents on the order plus the \$10 processing fee is less than \$50, the processing fee will be increased to bring the order amount up to the \$50 minimum. This processing fee will be applied before any applicable deposit account, quantity or member discounts have been applied. There is no minimum for orders containing only electronically delivered documents.



# There's more where this came from.

The American Petroleum Institute provides additional resources and programs to the oil and natural gas industry which are based on API® Standards. For more information, contact:

- |   |  |
|---|--|
| • API Monogram® Licensing Program                         | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • American Petroleum Institute Quality Registrar (APIQR®) | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API Spec Q1® Registration                               | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API Perforator Design Registration                      | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API ISO/TS 29001 Registration                           | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API Training Provider Certification Program             | Phone: 202-682-8490<br>Fax: 202-682-8070 |
| • Individual Certification Programs                       | Phone: 202-682-8064<br>Fax: 202-682-8348 |
| • Engine Oil Licensing and Certification System (EOLCS)   | Phone: 202-682-8516<br>Fax: 202-962-4739 |
| • API PetroTEAM™ (Training, Education and Meetings)       | Phone: 202-682-8195<br>Fax: 202-682-8222 |

Check out the API Publications, Programs, and Services Catalog online at [www.api.org](http://www.api.org).



American Petroleum Institute

Helping You Get  
The Job Done Right.®

Copyright American Petroleum Institute  
Provided by IHS under license with API  
No reproduction or networking permitted without license from IHS

Copyright American Petroleum Institute  
Provided by IHS under license with API  
No reproduction or networking permitted without license from IHS

Additional copies are available through Global Engineering Documents at (800) 854-7179 or (303) 397-7956

Information about API Publications, Programs and Services is available on the World Wide Web at: <http://www.api.org>



1220 L Street, Northwest  
Washington, D.C. 20005-4070

Product No. G05C62