



This Australian Standard was prepared by Committee ME/29, Fasteners. It was approved on behalf of the Council of Standards Australia on 10 April 2000 and published on 23 June 2000.

---

The following interests are represented on Committee ME/29:

Australian Building Codes Board  
Australian Chamber of Commerce and Industry  
Australian Industry Group  
Bureau of Steel Manufacturers of Australia  
Electricity Supply Association of Australia  
Federal Chamber of Automotive Industries  
Institute of Materials Engineering Australasia  
Metal Building Products Manufacturers Association

---

#### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, PO Box 1055, Strathfield, NSW 2135.

---

*This Standard was issued in draft form for comment as DR 00037.*

Australian Standard <sup>TM</sup>

**ISO metric hexagon bolts and screws—  
Product grades A and B**

**Part 2: Screws**

Originated as AS 1110—1972.  
Previous edition AS/NZS 1110:1995.  
Revised and redesignated, in part, as AS 1110.2—2000.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
PO Box 1055, Strathfield, NSW 2135, Australia

ISBN 0 7337 3400 6

## PREFACE

This Standard was prepared by the Standards Australia Committee ME/29, Fasteners to supersede AS/NZS 1110:1995, *ISO metric precision hexagon bolts and screws*, in part.

The objective of this Standard is to provide manufacturers, suppliers and users with the dimensions, tolerances and material requirements for hexagon head screws, ISO product grades A and B with ISO metric coarse threads.

This Standard is Part 2 of a two-part series on ISO metric hexagon bolts and screws. Part 1 gives the dimensions for bolts.

NOTE: The product grades refer to the quality of the product and to the size of the tolerances where grade A is the most precise and grade C is the least precise.

This Standard is identical with and has been reproduced from ISO 4017:1999, *Hexagon head screws—Product grades A and B*.

Statements expressed in mandatory terms in notes to tables and figures are deemed to be requirements of this Standard.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text 'this International Standard' should read 'this Australian Standard'.
- (c) A full point should be substituted for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to equivalent Australian Standards, as follows:

<i>Reference to International Standard</i>		<i>Australian Standard</i>	
ISO		AS	
225	Fasteners—Bolts, screws, studs and nuts—Symbols and designations of dimensions	—	
724	ISO general-purpose metric screw threads—Basic dimensions	—	
888	Bolts, screws and studs—Nominal lengths, and thread lengths for general purpose bolts	—	
898	Mechanical properties of fasteners made of carbon steel and alloy steel	4291	Mechanical properties of fasteners made of carbon steel and alloy steel
898-1	Part 1: Bolts, screws and studs	4291.1	Part 1: Bolts, screws and studs
965	ISO general purpose metric screw threads—Tolerances	—	
965-1	Part 1: Principles and basic data	—	
3269	Fasteners—Acceptance inspection	—	
3506	Mechanical properties of corrosion-resistant stainless steel-fasteners	—	
3506-1	Part 1: Bolts, screws and studs	—	
3508	Thread run-outs for fasteners with thread in accordance with ISO 261 and ISO 262	—	
4042	Fasteners—Electroplated coatings	—	

ISO		AS
4753	Fasteners—Ends of parts with external metric ISO thread	—
4759	Tolerances for fasteners	—
4759-1	Part 1: Bolts, screws, studs and nuts—Product grades A, B and C	—
6157	Fasteners—Surface discontinuities	—
8839	Mechanical properties of fasteners—Bolts, screws, studs and nuts made of non-ferrous metals	—
8992	Fasteners—General requirements for bolts, screws, studs and nuts	—
10683	Fasteners—Non-electrolytically applied zinc flake coatings	—

## CONTENTS

Page

Introduction.....	v
1 Scope.....	1
2 Normative references .....	1
3 Dimensions.....	3
4 Specifications and reference Standards.....	9
5 Designation.....	9
Bibliography.....	10

## INTRODUCTION

This International Standard is part of the complete ISO product standard series on external hexagon drive fasteners. The series comprises:

- a) hexagon head bolts (ISO 4014 to ISO 4016 and ISO 8765);
- b) hexagon head screws (ISO 4017, ISO 4018 and ISO 8676);
- c) hexagon nuts (ISO 4032 to ISO 4036, ISO 8673 to ISO 8675);
- d) hexagon bolts with flange (ISO 4162 and ISO 15071);
- e) hexagon nuts with flange (ISO 4161 and ISO 10663);
- f) structural and nuts (ISO 4775, ISO 7411 to ISO 7414 and ISO 7417).

NOTES

## AUSTRALIAN STANDARD

**ISO metric hexagon bolts and screws—Product grades A and B****Part 2:  
Screws****1 Scope**

This International Standard specifies the characteristics of hexagon head screws with threads from M1,6 up to and including M64, of product grade A for threads M1,6 to M24 and nominal lengths up to and including  $10d$  or 150 mm, whichever is shorter, and product grade B for threads over M24 or nominal lengths over  $10d$  or 150 mm, whichever is shorter.

NOTE This type of product is the same as that covered by ISO 4014 with the exception of threading up to head and nominal length up to and including 200 mm as popular lengths.

If, in special cases, specifications other than those listed in this International Standard are required, they should be selected from existing International Standards, for example ISO 724, ISO 888, ISO 898-1, ISO 965-1, ISO 3506-1, ISO 4753 and ISO 4759-1.

**2 Normative references**

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 225:1983, *Fasteners — Bolts, screws, studs and nuts — Symbols and designations of dimensions.*

ISO 724:1993, *ISO general-purpose metric screw threads — Basic dimensions.*

ISO 888:1976, *Bolts, screws and studs — Nominal lengths, and thread lengths for general purpose bolts.*

ISO 898-1:1999, *Mechanical properties of fasteners made of carbon steel and alloy steel — Part 1: Bolts, screws and studs.*

ISO 965-1:1998, *ISO general purpose metric screw threads — Tolerances — Part 1: Principles and basic data.*

ISO 3269:—<sup>1)</sup>, *Fasteners — Acceptance inspection.*

ISO 3506-1:1997, *Mechanical properties of corrosion-resistant stainless steel-fasteners — Part 1: Bolts, screws and studs.*

ISO 3508:1976, *Thread run-outs for fasteners with thread in accordance with ISO 261 and ISO 262.*

ISO 4042:1999, *Fasteners — Electroplated coatings.*

---

<sup>1)</sup> To be published. (Revision of ISO 3269:1988)

ISO 4753:—<sup>2)</sup>, *Fasteners — Ends of parts with external metric ISO thread.*

ISO 4759-1:—<sup>3)</sup>, *Tolerances for fasteners — Part 1: Bolts, screws, studs and nuts — Product grades A, B and C.*

ISO 6157-1:1988, *Fasteners — Surface discontinuities — Part 1: Bolts, screws and studs for general requirements.*

ISO 8839:1986, *Mechanical properties of fasteners — Bolts, screws, studs and nuts made of non-ferrous metals.*

ISO 8992:1986, *Fasteners — General requirements for bolts, screws, studs and nuts.*

ISO 10683:—<sup>4)</sup>, *Fasteners — Non-electrolytically applied zinc flake coatings.*

---

<sup>2)</sup> To be published. (Revision of ISO 4753:1983)

<sup>3)</sup> To be published. (Revision of ISO 4759-1:1978)


<sup>4)</sup> To be published.

### 3 Dimensions

See Figure 1 and Tables 1 and 2.

Symbols and description of dimensions are defined in ISO 225.

Dimensions in millimetres



- a  $\beta = 15^\circ$  to  $30^\circ$
- b Point shall be chamfered or for threads  $\leq M4$  may be as-rolled (sheared end) (see ISO 4753)
- c Incomplete thread  $u \leq 2P$
- d Reference datum for  $d_w$
- e  $d_s \approx$  pitch diameter

Figure 1

Table 1 — Preferred threads

Dimensions in millimetres

Threads ( <i>d</i> )			M1,6	M2	M2,5	M3	M4	M5	M6
<i>p<sub>a</sub></i>			0,35	0,4	0,45	0,5	0,7	0,8	1
<i>a</i>		max. <sup>b</sup>	1,05	1,2	1,35	1,5	2,1	2,4	3
		min.	0,35	0,4	0,45	0,5	0,7	0,8	1
<i>c</i>		max.	0,25	0,25	0,25	0,40	0,40	0,50	0,50
		min.	0,10	0,10	0,10	0,15	0,15	0,15	0,15
<i>d<sub>a</sub></i>		max.	2	2,6	3,1	3,6	4,7	5,7	6,8
<i>d<sub>w</sub></i>	Product grade	A min.	2,27	3,07	4,07	4,57	5,88	6,88	8,88
		B	2,30	2,95	3,95	4,45	5,74	6,74	8,74
<i>e</i>	Product grade	A min.	3,41	4,32	5,45	6,01	7,66	8,79	11,05
		B	3,28	4,18	5,31	5,88	7,50	8,63	10,89
<i>k</i>	Product grade	nom.	1,1	1,4	1,7	2	2,8	3,5	4
		A max.	1,225	1,525	1,825	2,125	2,925	3,65	4,15
	min.	0,975	1,275	1,575	1,875	2,675	3,35	3,85	
	B max.	1,3	1,6	1,9	2,2	3,0	3,74	4,24	
<i>k<sub>w</sub><sup>c</sup></i>	Product grade	A min.	0,68	0,89	1,10	1,31	1,87	2,35	2,70
		B	0,63	0,84	1,05	1,26	1,82	2,28	2,63
<i>r</i>		min.	0,1	0,1	0,1	0,1	0,2	0,2	0,25
<i>s</i>	Product grade	nom. = max.	3,20	4,00	5,00	5,50	7,00	8,00	10,00
		A min.	3,02	3,82	4,82	5,32	6,78	7,78	9,78
		B	2,90	3,70	4,70	5,20	6,64	7,64	9,64
Product grade									
A   B									
l									
nom.	min.	max.	min.	max.					
2	1,8	2,2	—	—					
3	2,8	3,2	—	—					
4	3,76	4,24	—	—					
5	4,76	5,24	—	—					
6	5,76	6,24	—	—					
8	7,71	8,29	—	—					
10	9,71	10,29	—	—					
12	11,65	12,35	—	—					
16	15,65	16,35	—	—					
20	19,58	20,42	18,95	21,05					
25	24,58	25,42	23,95	26,05					
30	29,58	30,42	28,95	31,05					
35	34,5	35,5	33,75	36,25					
40	39,5	40,5	38,75	41,25					
45	44,5	45,5	43,75	46,25					
50	49,5	50,5	48,75	51,25					
55	54,4	55,6	53,5	56,5					
60	59,4	60,6	58,5	61,5					
65	64,4	65,6	63,5	66,5					
70	69,4	70,6	68,5	71,5					
80	79,4	80,6	78,5	81,5					
90	89,3	90,7	88,25	91,75					
100	99,3	100,7	98,25	101,75					
110	109,3	110,7	108,25	111,75					
120	119,3	120,7	118,25	121,75					
130	129,2	130,8	128	132					
140	139,2	140,8	138	142					
150	149,2	150,8	148	152					
160	—	—	158	162					
180	—	—	178	182					
200	—	—	197,7	202,3					

Thread (d)			M8	M10	M12	M16	M20	M24
$p^a$			1,25	1,5	1,75	2	2,5	3
$a$	max. <sup>b</sup>		4	4,5	5,3	6	7,5	9
		min.	1,25	1,5	1,75	2	2,5	3
$c$	max.		0,60	0,60	0,60	0,8	0,8	0,8
		min.	0,15	0,15	0,15	0,2	0,2	0,2
$d_a$		max.	9,2	11,2	13,7	17,7	22,4	26,4
$d_w$	Product grade	A min.	11,63	14,63	16,63	22,49	28,19	33,61
		B	11,47	14,47	16,47	22	27,7	33,25
$e$	Product grade	A min.	14,38	17,77	20,03	26,75	33,53	39,98
		B	14,20	17,59	19,85	26,17	32,95	39,55
$k$	Product grade	nom.	5,3	6,4	7,5	10	12,5	15
		A max.	5,45	6,58	7,68	10,18	12,715	15,215
	min.	5,15	6,22	7,32	9,82	12,285	14,785	
	B max.	5,54	6,69	7,79	10,29	12,85	15,35	
Product grade	min.	5,06	6,11	7,21	9,71	12,15	14,65	
	A min.	3,61	4,35	5,12	6,87	8,6	10,35	
$k_w^c$	Product grade	B	3,54	4,28	5,05	6,8	8,51	10,26
		min.	0,4	0,4	0,6	0,6	0,8	0,8
$r$		min.	0,4	0,4	0,6	0,6	0,8	0,8
$s$	Product grade	nom. = max.	13,00	16,00	18,00	24,00	30,00	36,00
		A min.	12,73	15,73	17,73	23,67	29,67	35,38
		B	12,57	15,57	17,57	23,16	29,16	35,00
Product grade								
A								
B								
l								
nom.	min.	max.	min.	max.				
2	1,8	2,2	—	—				
3	2,8	3,2	—	—				
4	3,76	4,24	—	—				
5	4,76	5,24	—	—				
6	5,76	6,24	—	—				
8	7,71	8,29	—	—				
10	9,71	10,29	—	—				
12	11,65	12,35	—	—				
16	15,65	16,35	—	—				
20	19,58	20,42	18,95	21,05				
25	24,58	25,42	23,95	26,05				
30	29,58	30,42	28,95	31,05				
35	34,5	35,5	33,75	36,25				
40	39,5	40,5	38,75	41,25				
45	44,5	45,5	43,75	46,25				
50	49,5	50,5	48,75	51,25				
55	54,4	55,6	53,5	56,5				
60	59,4	60,6	58,5	61,5				
65	64,4	65,6	63,5	66,5				
70	69,4	70,6	68,5	71,5				
80	79,4	80,6	78,5	81,5				
90	89,3	90,7	88,25	91,75				
100	99,3	100,7	98,25	101,75				
110	109,3	110,7	108,25	111,25				
120	119,3	120,7	118,25	121,75				
130	129,2	130,8	128	132				
140	139,2	140,8	138	142				
150	149,2	150,8	148	152				
160	—	—	158	162				
180	—	—	178	182				
200	—	—	197,7	202,3				

Table 1 (continued)

Thread ( <i>d</i> )			M30	M36	M42	M48	M56	M64
$p^a$			3,5	4	4,5	5	5,5	6
$a$	max. <sup>b</sup>		10,5	12	13,5	15	16,5	18
		min.	3,5	4	4,5	5	5,5	6
$c$	max.		0,8	0,8	1,0	1,0	1,0	1,0
		min.	0,2	0,2	0,3	0,3	0,3	0,3
$d_a$		max.	33,4	39,4	45,6	52,6	63	71
$d_w$	Product grade	A min.	—	—	—	—	—	—
		B	42,75	51,11	59,95	69,45	78,66	88,16
$e$	Product grade	A min.	—	—	—	—	—	—
		B	50,85	60,79	71,3	82,6	93,56	104,86
$k$	Product grade	nom.	18,7	22,5	26	30	35	40
		A max.	—	—	—	—	—	—
	Product grade	B max.	19,12	22,92	26,42	30,42	35,5	40,5
		min.	18,28	22,08	25,58	29,58	34,5	39,5
$k_w^c$	Product grade	A min.	—	—	—	—	—	—
		B	12,8	15,46	17,91	20,71	24,15	27,65
$r$		min.	1	1	1,2	1,6	2	2
$s$	Product grade	nom. = max.	46	55,0	65,0	75,0	85,0	95,0
		A min.	—	—	—	—	—	—
		B	45	53,8	63,1	73,1	82,8	92,8
Product grade								
A B								
/								
nom.	min.	max.	min.	max.				
2	1,8	2,2	—	—				
3	2,8	3,2	—	—				
4	3,76	4,24	—	—				
5	4,76	5,24	—	—				
6	5,76	6,24	—	—				
8	7,71	8,29	—	—				
10	9,71	10,29	—	—				
12	11,65	12,35	—	—				
16	15,65	16,35	—	—				
20	19,58	20,42	18,95	21,05				
25	24,58	25,42	23,95	26,05				
30	29,58	30,42	28,95	31,05				
35	34,5	35,5	33,75	36,25				
40	39,5	40,5	38,75	41,25				
45	44,5	45,5	43,75	46,25				
50	49,5	50,5	47,75	51,25				
55	54,4	55,6	53,5	56,5				
60	59,4	60,6	58,5	61,5				
65	64,4	65,6	63,5	66,5				
70	69,4	70,6	68,5	71,5				
80	79,4	80,6	78,5	81,5				
90	89,3	90,7	88,25	91,75				
100	99,3	100,7	98,25	101,75				
110	109,3	110,7	108,25	111,75				
120	119,3	120,7	118,25	121,75				
130	129,2	130,8	128	132				
140	139,2	140,8	138	142				
150	149,2	150,8	148	152				
160	—	—	158	162				
180	—	—	178	182				
200	—	—	197,7	202,3				

NOTE Range of popular lengths between the solid, boldface stepped line:  
 — for product grade A, above the dashed, stepped line;  
 — for product grade B, below this line.

<sup>a</sup>  $p$  is the pitch of the thread.

<sup>b</sup> Values in accordance with  $u_{max}$ , normal series, in ISO 3508.

<sup>c</sup>  $k_{w, min} = 0,7 k_{min}$

Table 2 — Non-preferred threads

Dimensions in millimetres

Thread ( <i>d</i> )		M3,5	M14	M18	M22	M27	
$p^a$		0,6	2	2,5	2,5	3	
<i>a</i>	max. <sup>b</sup>	1,8	6	7,5	7,5	9	
	min.	0,6	2	2,5	2,5	3	
<i>c</i>	max.	0,40	0,60	0,8	0,8	0,8	
	min.	0,15	0,15	0,2	0,2	0,2	
<i>d<sub>a</sub></i>	max.	4,1	15,7	20,2	24,4	30,4	
<i>d<sub>w</sub></i>	Product grade	A min.	5,07	19,64	25,34	31,71	—
		B	4,95	19,15	24,85	31,35	38
<i>e</i>	Product grade	A min.	6,58	23,36	30,14	37,72	—
		B	6,44	22,78	29,56	37,29	45,2
<i>k</i>	Product grade	nom.	2,4	8,8	11,5	14	17
		A max.	2,525	8,98	11,715	14,215	—
	min.	2,275	8,62	11,285	13,785	—	
	Product grade	B max.	2,6	9,09	11,85	14,35	17,35
		min.	2,2	8,51	11,15	13,65	16,65
	<i>k<sub>w</sub><sup>c</sup></i>	Product grade	A min.	1,59	6,03	7,9	9,65
B			1,54	5,96	7,81	9,56	11,66
<i>r</i>	min.	0,1	0,6	0,6	0,8	1	
	nom. = max.	6,00	21,00	27,00	34,00	41	
<i>s</i>	Product grade	A min.	5,82	20,67	26,67	33,38	—
		B	5,70	20,16	26,16	33,00	40
		Product grade					
		A	B				
		<i>l</i>					
nom.	min.	max.	min.	max.			
8	7,71	8,29	—	—			
10	9,71	10,29	—	—			
12	11,65	12,35	—	—			
16	15,65	16,35	—	—			
20	19,58	20,42	—	—			
25	24,58	25,42	—	—			
30	29,58	30,42	—	—			
35	34,5	35,5	—	—			
40	39,5	40,5	38,75	41,25			
45	44,5	45,5	43,75	46,25			
50	49,5	50,5	48,75	51,25			
55	54,4	55,6	53,5	56,5			
60	59,4	60,6	58,5	61,5			
65	64,4	65,6	63,5	66,5			
70	69,4	70,6	68,5	71,5			
80	79,4	80,6	78,5	81,5			
90	89,3	90,7	88,25	91,75			
100	99,3	100,7	98,25	101,75			
110	109,3	110,7	108,25	111,75			
120	119,3	120,7	118,25	121,75			
130	129,2	130,8	128	132			
140	139,2	140,8	138	142			
150	149,2	150,8	148	152			
160	—	—	158	162			
180	—	—	178	182			
200	—	—	197,7	202,3			

Table 2 (continued)

Thread ( <i>d</i> )		M33	M39	M45	M52	M60	
$p^a$		3,5	4	4,5	5	5,5	
<i>a</i>	max. <sup>b</sup>	10,5	12	13,5	15	16,5	
	min.	3,5	4	4,5	5	5,5	
<i>c</i>	max.	0,8	1,0	1,0	1,0	1,0	
	min.	0,2	0,3	0,3	0,3	0,3	
$d_a$		max.	36,4	42,4	48,6	56,6	67
$d_w$	Product grade	A min.	—	—	—	—	—
		B	46,55	55,86	64,7	74,2	83,41
<i>e</i>	Product grade	A min.	—	—	—	—	—
		B	55,37	66,44	76,95	88,25	99,21
<i>k</i>	Product grade	nom.	21	25	28	33	38
		A min.	—	—	—	—	—
	Product grade	max.	—	—	—	—	—
		B max.	21,42	25,42	28,42	33,5	38,5
		min.	20,58	24,58	27,58	32,5	37,5
$k_w^c$	Product grade	A min.	—	—	—	—	—
		B	14,41	17,21	19,31	22,75	26,25
<i>r</i>	min.	1	1	1,2	1,6	2	
		nom. = max.	50	60,0	70,0	80,0	90,0
<i>s</i>	Product grade	A min.	—	—	—	—	—
		B	49	58,8	68,1	78,1	87,8
		Product grade					
		A	B				
		<i>l</i>					
nom.	min.	max.	min.	max.			
8	7,71	8,29	—	—			
10	9,71	10,29	—	—			
12	11,65	12,35	—	—			
16	15,65	16,35	—	—			
20	19,58	20,42	—	—			
25	24,58	25,42	—	—			
30	29,58	30,42	—	—			
35	34,5	35,5	—	—			
40	39,5	40,5	38,75	41,25			
45	44,5	45,5	43,75	46,25			
50	49,5	50,5	48,75	51,25			
55	54,4	55,6	53,5	56,5			
60	59,4	60,6	58,5	61,5			
65	64,4	65,6	63,5	66,5			
70	69,4	70,6	68,5	71,5			
80	79,4	80,6	78,5	81,5			
90	89,3	90,7	88,25	91,75			
100	99,3	100,7	98,25	101,75			
110	109,3	110,7	108,25	111,75			
120	119,3	120,7	118,25	121,75			
130	129,2	130,8	128	132			
140	139,2	140,8	138	142			
150	149,2	150,8	148	152			
160	—	—	158	162			
180	—	—	178	182			
200	—	—	197,7	202,3			
NOTE Range of popular lengths between the solid, boldface stepped line:							
— for product grade A, above the dashed, stepped line;							
— for product grade B, below this line.							
<sup>a</sup> <i>p</i> is the pitch of the thread.							
<sup>b</sup> Values in accordance with $a_{max}$ normal series, in ISO 3508.							
<sup>c</sup> $k_{w, min} = 0,7 k_{min}$							

## 4 Specifications and reference standards

See Table 3.

**Table 3 — Specifications and reference standards**

Material		Steel	Stainless steel	Non-ferrous metal
<b>General requirements</b>	International Standard	ISO 8992		
	Tolerance	6g		
<b>Thread</b>	International Standards	ISO 724, ISO 965-1		
	Property class <sup>a</sup>	$d < 3$ mm: as agreed $3 \text{ mm} \leq d \leq 39$ mm: 5.6, 8.8, 9.8, 10.9 $d > 39$ mm: as agreed	$d \leq 24$ mm: A2-70, A4-70 $24 \text{ mm} < d \leq 39$ mm: A2-50, A4-50 $d > 39$ mm: as agreed	Materials specified in ISO 8839
International Standards	$d \leq 39$ mm: ISO 898-1 $d < 3$ mm and $d > 39$ mm: as agreed	$d \leq 39$ mm: ISO 3506-1 $d > 39$ mm: as agreed		
<b>Tolerances</b>	Product grade	For $d \leq 24$ mm and $l \leq 10 d$ or 150 mm <sup>b</sup> : A For $d > 24$ mm or $l > 10 d$ or 150 mm <sup>b</sup> : B		
	International Standard	ISO 4759-1		
<b>Finish and/or coating</b>		As processed  Requirements for electroplating are covered in ISO 4042  Requirements for non-electrolytically applied zinc flake coatings are covered in ISO 10683  If different electroplating requirements are desired or if requirements are needed for other finishes, they should be agreed between customer and supplier  Limits for surface discontinuities are covered in ISO 6157-1	Plain	Plain  Requirements for electroplating are covered in ISO 4042
<b>Acceptability</b>		For acceptance procedure, see ISO 3269.		
<sup>a</sup> For other property classes see ISO 898-1 for steel and ISO 3506-1 for stainless steel respectively. <sup>b</sup> Whichever is shorter.				

## 5 Designation

### EXAMPLE

A hexagon head screw with thread size M12, nominal length  $l = 80$  mm and property class 8.8 is designated as follows:

**Hexagon head screw ISO 4017 - M12 × 80 - 8.8**

## Bibliography

- [1] ISO 4014:1999, *Hexagon head bolts — Product grades A and B.*
- [2] ISO 4015:1979, *Hexagon head bolts — Product grade B — Reduced shank (shank diameter approximately equal to pitch diameter).*
- [3] ISO 4016:1999, *Hexagon head bolts — Product grade C.*
- [4] ISO 4018:1999, *Hexagon head screws — Product grade C.*
- [5] ISO 4032:1999, *Hexagon nuts, style 1 — Product grades A and B.*
- [6] ISO 4033:1999, *Hexagon nuts, style 2 — Product grades A and B.*
- [7] ISO 4034:1999, *Hexagon nuts — Product grade C.*
- [8] ISO 4035:1999, *Hexagon thin nuts (chamfered) — Product grades A and B.*
- [9] ISO 4036:1999, *Hexagon thin nuts (unchamfered) — Product grade B.*
- [10] ISO 4161:1999, *Hexagon nuts with flange — Coarse thread.*
- [11] ISO 4162:—<sup>5)</sup>, *Hexagon bolts with flange — Small series — Product grade combination A/B.*
- [12] ISO 4775:1984, *Hexagon nuts for high-strength structural bolting with large width across flats — Product grade B — Property classes 8 and 10.*
- [13] ISO 7411:1984, *Hexagon bolts for high-strength structural bolting with large width across flats (thread lengths according to ISO 888) — Product grade C — Property classes 8.8 and 10.9.*
- [14] ISO 7412:1984, *Hexagon bolts for high-strength structural bolting with large width across flats (short thread length) — Product grade C — Property classes 8.8 and 10.9.*
- [15] ISO 7413:1984, *Hexagon nuts for structural bolting, style 1, hot-dip galvanize (oversize tapped) — Product grades A and B — Property classes 5, 6 and 8.*
- [16] ISO 7414:1984, *Hexagon nuts for structural bolting with large width across flats, style 1 — Product grade B — Property class 10.*
- [17] ISO 7417:1984, *Hexagon nuts for structural bolting, style 2, hot-dip galvanize (oversize tapped) — Product grade A — Property class 9.*
- [18] ISO 8673:1999, *Hexagon nuts, style 1, with metric fine pitch thread — Product grades A and B.*
- [19] ISO 8674:1999, *Hexagon nuts, style 2, with metric fine pitch thread — Product grades A and B.*
- [20] ISO 8675:1999, *Hexagon thin nuts (chamfered) with metric fine pitch thread — Product grades A and B.*
- [21] ISO 8676:1999, *Hexagon head screws with metric fine pitch thread — Product grades A and B.*

---

<sup>5)</sup> To be published. (Revision of ISO 4162:1990)

[22] ISO 8765:1999, *Hexagon head bolts with metric fine pitch thread — Product grades A and B.*

[23] ISO 10663:1999, *Hexagon nuts with flange — Fine pitch thread.*

[24] ISO 15071:1999, *Hexagon bolts with flange — Small series — Product grade A.*

### **Standards Australia**

Standards Australia is an independent company, limited by guarantee, which prepares and publishes most of the voluntary technical and commercial standards used in Australia. These standards are developed through an open process of consultation and consensus, in which all interested parties are invited to participate. Through a Memorandum of Understanding with the Commonwealth government, Standards Australia is recognized as Australia's peak national standards body.

### **Australian Standards**

Australian Standards are prepared by committees of experts from industry, governments, consumers and other relevant sectors. The requirements or recommendations contained in published Standards are a consensus of the views of representative interests and also take account of comments received from other sources. They reflect the latest scientific and industry experience. Australian Standards are kept under continuous review after publication and are updated regularly to take account of changing technology.

### **International Involvement**

Standards Australia is responsible for ensuring that the Australian viewpoint is considered in the formulation of international Standards and that the latest international experience is incorporated in national Standards. This role is vital in assisting local industry to compete in international markets. Standards Australia represents Australia at both ISO (The International Organization for Standardization) and the International Electrotechnical Commission (IEC).

### **Electronic Standards**

All Australian Standards are available in electronic editions, either downloaded individually from our Web site, or via on-line and CD ROM subscription services. For more information phone 1300 65 46 46 or visit us at

[www.standards.com.au](http://www.standards.com.au)



**S t a n d a r d s A u s t r a l i a**

PO Box 1055 Strathfield NSW 2135

**Administration** Phone (02) 9746 4700 Fax (02) 9746 8450 Email [mail@standards.com.au](mailto:mail@standards.com.au)

**Customer Service** Phone 1300 65 46 46 Fax 1300 65 49 49 Email [sales@standards.com.au](mailto:sales@standards.com.au)

**Internet** [www.standards.com.au](http://www.standards.com.au)

This page has been left intentionally blank.