

Australian/New Zealand Standard™

Method of test for pulp and paper

**Method 421: Paper, board and pulps —
Determination of pH of aqueous extracts
— Cold extraction**



AS/NZS 1301.421:2020

This Joint Australian/New Zealand Standard™ was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 17 June 2020 and by the New Zealand Standards Approval Board on 1 July 2020.

This Standard was published on 10 July 2020.

The following are represented on Committee PK-019:

Appita
Monash University
New Zealand Paper Forum
Scion

This Standard was issued in draft form for comment as DR AS/NZS 1301.421:2020.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

www.standards.govt.nz

ISBN 978 1 76072 925 7

Australian/New Zealand Standard™

Method of test for pulp and paper

Method 421: Paper, board and pulps — Determination of pH of aqueous extracts — Cold extraction

Originated as AS/NZS 1301.421:2008.
Second edition 2020.

COPYRIGHT

© ISO 2020 — All rights reserved
© Standards Australia Limited/the Crown in right of New Zealand, administered by the New Zealand Standards Executive 2020

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth) or the Copyright Act 1994 (New Zealand).

Preface

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper to supersede AS/NZS 1301.421:2008, *Methods of test for pulp and paper — Method 421: Determination of pH of aqueous extracts — Cold extraction method*.

The objective of this document is to specify a method for the determination of the pH-value defined by the electrolytes extractable by cold water from a sample of paper, board or pulp.

This document is applicable to all types of paper, board and pulp.

For cellulosic papers used for electrical purposes, the method used should be that given in IEC 60554-2.

This document is identical with, and has been reproduced from, ISO 6588-1:2020, *Paper, board and pulps — Determination of pH of aqueous extracts — Part 1: Cold extraction*.

As this document has been reproduced from an International Standard, a full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface	ii
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	2
6 Apparatus and equipment	2
7 Sampling and preparation of sample	2
7.1 Sampling	2
7.2 Preparation of sample	2
8 Procedure	2
8.1 Weighing	3
8.2 Extraction	3
8.3 Determination of pH	3
9 Calculation	3
10 Test report	3
Annex A (informative) Preparation of some standard buffer solutions	5
Annex B (informative) Precision	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 6588-1:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

— addition of the last four paragraphs in the Introduction to clarify the differences, in the role and mode of addition of a salt solution, between this document and ISO 29681[5].

A list of all parts in the ISO 6588 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Kraft fibre is well known to contain ionisable groups that are fixed to or in the fibre wall. In order to fulfil the electro-neutrality, these groups are balanced by an equivalent number of positive charges, which can be either protons or various metal ions. Especially in pulp suspensions at low ionic strengths, this can give rise to a marked uneven distribution of mobile ions between the volume held by the fibre wall and the bulk suspension liquor. This means that the fibre acts as an ion exchanger. These ion-exchange phenomena can be modelled very well with the Donnan theory^{[2][3]}.

If a relatively clean pulp fibre sample, for example bleached dried pulp, is diluted in deionised water, the result will be a pulp suspension with a very low ionic strength. In such a system, most of the cations present, including protons, will be concentrated in the water volume held by the fibre wall. If the pH is measured, it will be measured in the bulk suspension liquor. By adding salt to this kind of system, the ion exchange phenomena will be decreased, and the concentration of different cations will be the same in the water held by the fibre wall and in the bulk suspension liquor. Since the process waters always contain a certain amount of ions, such a salt addition will give a more realistic environment when measuring the pH of relatively clean pulp samples.

Based on the foregoing, two ISO Standards, ISO 6588-1 and ISO 29681, are available for determination of the pH of cold aqueous extracts of paper, board, or pulps. In ISO 29681, a salt solution is added prior to extraction; however, in ISO 6588-1, the extraction is carried out with distilled or deionized water. ISO 29681 is specifically applicable to bleached pulps from virgin fibres and to pulp samples having a low ionic strength for which the pH-value will give more realistic results related to mill conditions than those obtained with ISO 6588-1.

It is necessary to be aware that the results will not be the same when measuring pH according to ISO 6588-1 and to ISO 29681. The difference can be significant especially when measuring pulps having a low ionic strength.

ISO 6588-2 differs from this document only as regards the extraction conditions. No general guidance can be given as to which of the two procedures (hot or cold) is best suited in a particular situation.

It should be noted that in ISO 6588-1, addition of a salt solution is performed after extraction and filtration only for the purpose of obtaining a more stable and accurate pH measurement.

NOTES

Australian/New Zealand Standard

Method of test for pulp and paper

Method 421: Paper, board and pulps — Determination of pH of aqueous extracts — Cold extraction

1 Scope

This document specifies a method for the determination of the pH-value defined by the electrolytes extractable by cold water from a sample of paper, board or pulp.

This document is applicable to all types of paper, board and pulp.

As the quantity of extractable ionic material approaches zero, as in the case of highly purified pulps, the precision of the method becomes poor because of the difficulties encountered in making pH measurements on water containing little electrolytic material.

Since the extraction in this document is performed with distilled or deionised water, the pH-value measured will sometimes be different (e.g. for fully bleached pulp) from the pH-value measured under mill process conditions in which various types of process waters, e.g. chemically treated river water containing electrolytes, are used. In such cases, ISO 29681 should be used instead, as it is specifically applicable to bleached pulps from virgin fibres and to pulp samples having a low ionic strength for which the pH value will give more realistic results related to mill conditions than those obtained with this document.

For cellulosic papers used for electrical purposes, the method used should be that given in IEC 60554-2[4].

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 7213, *Pulps — Sampling for testing*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.iso.org/obp>

4 Principle

Extraction of a sample of 2 g for 1 h with 100 ml of cold water of high purity. Filtration of the extract and addition of a salt solution. Measurement of the pH-value of the extract at a temperature between 20 °C and 25 °C.

5 Reagents

5.1 Water, distilled or deionised water shall be used throughout the test. The conductivity of the water shall not exceed 0,1 mS/m, after boiling for 1 h and cooling in an acid-free atmosphere (e.g. free of CO₂, SO₂, H₂S) to a temperature between 20 °C and 25 °C. The pH of the water should be in the range of 6,8 to 7,3. Instructions for the determination of conductivity are specified in ISO 3696.

5.2 Standard buffer solutions, with known pH-values of about 4, 7 and 9. Such buffer solutions are commercially available. Some examples of suitable buffer solutions are given, and their preparation is described, in [Annex A](#).

5.3 Potassium chloride solution, 1M. Dissolve 7,4 g of KCl, analytical grade, into 100 ml of freshly boiled, distilled water. Prepare a fresh solution every week.

6 Apparatus and equipment

Use the following, in addition to ordinary laboratory apparatus and equipment.

6.1 Glassware of chemically resistant glass, flasks with ground-glass joints, stoppers, beakers and fritted glass filter. All glassware shall be cleaned with an acid cleaning solution, without the use of soap or detergent, and they shall be carefully rinsed with water ([5.1](#)) and allowed to dry before use.

6.2 pH-meter, fitted with glass and calomel electrodes or with a combined electrode, capable of being read to at least 0,05 pH-unit.

7 Sampling and preparation of sample

7.1 Sampling

The sampling procedure to be followed depends on the particular circumstances in each case. If the analysis is being made to evaluate a lot or a consignment of pulp, paper or board, the sample shall be taken in accordance with ISO 7213 or ISO 186, as relevant. If the analysis is made on another type of sample, report the origin of the sample and, if possible, the sampling procedure, and ensure that the specimen taken in [7.1](#) is representative of the sample received.

Wear clean protective gloves when handling the sample.

NOTE Some gloves are powdered to prevent them from sticking to one another, and this powder can cause contamination of the sample.

7.2 Preparation of sample

Do not touch the sample with bare hands and ensure that it has been placed only on clean surfaces. Cut the sample with a knife or cutter, or tear it, into pieces approximately 1 cm² in size. Split samples of heavy board.

Mix the pieces thoroughly. Store the pieces in clean, covered containers.

8 Procedure

Run the procedure in duplicate.

8.1 Weighing

Weigh $2,0 \text{ g} \pm 0,1 \text{ g}$ of air-dry sample (6.2) in a 250 ml flask (5.1).

NOTE Since the amount of sample is not critical, there is no need to determine the dry matter content to adjust for minor differences in moisture content.

8.2 Extraction

Add 100 ml of water (5.1) to the flask (6.1) containing the sample pieces. Check that all pieces are soaked. Seal the flask with its ground-glass stopper and leave it to stand for 1 h at a temperature between 20 °C and 25 °C. Shake the flask at least once during this time.

Filter the extract through a coarse, fritted glass filter into a small beaker (6.1). Immediately add 2 ml of potassium chloride solution (5.3) and continue with the measurement.

8.3 Determination of pH

Operate the pH-meter in accordance with the manufacturer's instruction. Wash the electrodes with water (5.1); allow the water to drain from the electrodes, but do not wipe them. Calibrate the pH-meter (5.2), at a temperature between 20 °C and 25 °C, with two different buffer solutions (5.2) having pH-values such that the pH of the extract is between the pH-values of the buffer solutions. The first buffer solution shall be chosen so that the pH-value of the buffer solution is in the same region as the electric zero point of the pH-meter (usually = 7). The reading for the second buffer solution should agree with its correct value to within 0,1 pH-unit.

If the pH-meter fails to show the correct pH-value for the second buffer solution, consult the manufacturer's manual. A deviation of, or exceeding, 0,2 pH-units, rounded to the nearest 0,1 pH unit, indicates a faulty electrode. In addition, a slow but continuous increase or decrease in the reading indicates a faulty electrode.

After calibration, rinse the electrodes several times with water (5.1) and once in a small quantity of the extract. Check that the temperature of the extract is between 20 °C and 25 °C. Immerse the electrodes in the extract. Record the pH when there is no measurable drift, within 30 s.

Before measuring the next sample, rinse the electrodes carefully with water (5.1) to remove any traces of sample or buffer solution.

At the end of a series of measurements, check the electrodes with the same buffer solutions. The results for both solutions should agree with their correct value to within 0,1 pH unit. Otherwise repeat the procedure in 8.3.

9 Calculation

Calculate the mean of the duplicate determinations.

Report the pH-value to the nearest 0,1 pH-unit. The individual results should not differ by more than 0,2 pH-unit; if they do, repeat the determination with two additional extracts, and report the mean and the range of all measurements.

NOTE See Annex B for precision.

10 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 6588-1;
- b) the date and place of testing;

- c) all the information necessary for complete identification of the sample;
- d) the result, expressed as indicated in [Clause 8](#);
- e) any unusual features observed in the course of the test;
- f) any departure from the procedure described in this document, or any other circumstances which may have affected the result.

Annex A

(informative)

Preparation of some standard buffer solutions

All the reagents used shall be of recognized reagent grade. The buffer solutions shall be renewed at least once a month. The anhydrous salts in [A.1](#) and [A.2](#) shall be dried at 120 °C.

A.1 Buffer solution pH 4,0: Potassium hydrogen phthalate, 0,05 mol/l solution

Dissolve 10,21 g of potassium hydrogen phthalate ($\text{KHC}_8\text{H}_4\text{O}_4$) in water ([5.1](#)) in a 1 litre volumetric flask and dilute to the mark.

The pH-value of this solution is 4,00 at 20 °C and 4,01 at 25 °C.

A.2 Buffer solution pH 6,9: Potassium dihydrogen phosphate and disodium hydrogen phosphate solution

Dissolve 3,39 g of potassium dihydrogen phosphate (KH_2PO_4) and 3,54 g disodium hydrogen phosphate (Na_2HPO_4) in water ([5.1](#)) in a 1 litre volumetric flask and dilute to the mark.

The pH-value of this solution is 6,87 at 20 °C and 6,86 at 25 °C.

A.3 Buffer solution pH 9,2: Disodium tetraborate solution

Dissolve 3,80 g of disodium tetraborate decahydrate ($\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$) in water ([5.1](#)) in a 1 litre volumetric flask and dilute to the mark.

The pH-value of this solution is 9,23 at 20 °C and 9,18 at 25 °C.

Annex B (informative)

Precision

B.1 General

In February 2002, an international round-robin was performed in which 5 laboratories from different countries participated.

The calculations have been made according to ISO/TR 24498[6].

The repeatability and reproducibility limits reported are estimates of the maximum difference which should be expected in 19 of 20 instances, when comparing two test results for material similar to those described under similar test conditions. These estimates may not be valid for different materials or different test conditions.

NOTE Repeatability and reproducibility limits are calculated by multiplying the repeatability and reproducibility standard deviations by 2,77, where $2,77 = 1,96\sqrt{2}$.

B.2 Repeatability

The pH-values of four different samples were determined in one laboratory according to this document. Ten determinations were made in each case. Mean values, standard deviations and coefficients of variations as well as repeatability limits for each type of sample are shown in [Table B.1](#).

Table B.1 — Repeatability

Sample	Mean value pH	Standard deviation s_r	Coefficient of variation $C_{V,r} (\%)$	Repeatability limit r
Copy paper	9,9	0,01	0,07	0,03
Paperboard	7,8	0,07	0,84	0,19
Bleached pulp	5,2	0,02	0,42	0,06
Unbleached pulp	7,4	0,03	0,46	0,08

B.3 Reproducibility

The pH-values of four different samples were determined in five different laboratories according to this document. Mean values, standard deviations and coefficients of variations, as well as reproducibility limits, for each type of sample, based on the results of five laboratories, are shown in [Table B.2](#).

Table B.2 — Reproducibility

Sample	Mean value pH	Standard deviation s_R	Coefficient of variation $C_{V,R} (\%)$	Reproducibility limit R
Copy paper	9,8	0,22	2,2	0,61
Paperboard	7,8	0,34	4,4	0,94
Bleached pulp	5,7	0,73	12,8	2,02
Unbleached pulp	7,3	0,26	3,6	0,72

Bibliography

- [1] ISO 6588-2, *Paper, board and pulps — Determination of pH of aqueous extracts — Part 2: Hot extraction*
- [2] SCALLAN A.M. In: The pH inside the fibre wall. Cellulose Sources and Exploitation. (KENNEDY J.F., PHILIPS G.O., WILLIAMS P.A. eds.). Eric Horwood, London, 1990, pp. 211
- [3] SCALLAN A.M. Predicting the Ion-Exchange of Kraft Pulp Using Donnan Theory. *Journal of Pulp and Paper Science*. 1996, **22** (9) pp. J332–J337
- [4] IEC 60554-2, *Cellulosic papers for electrical purposes — Part 2: Methods of test*
- [5] ISO 29681, *Paper, board and pulps — Determination of pH of salted water extracts*
- [6] ISO/TR 24498, *Paper, board and pulps — Estimation of uncertainty for test methods by interlaboratory comparisons*
- [7] ISO 3696, *Water for analytical laboratory use — Specification and test methods*

Standards Australia

Standards Australia is an independent company, limited by guarantee, which prepares and publishes most of the voluntary technical and commercial standards used in Australia. These standards are developed through an open process of consultation and consensus, in which all interested parties are invited to participate. Through a Memorandum of Understanding with the Commonwealth government, Standards Australia is recognized as Australia's peak national standards body.

Standards New Zealand

The first national Standards organization was created in New Zealand in 1932. The New Zealand Standards Executive is established under the Standards and Accreditation Act 2015 and is the national body responsible for the production of Standards.

Australian/New Zealand Standards

Under a Memorandum of Understanding between Standards Australia and Standards New Zealand, Australian/New Zealand Standards are prepared by committees of experts from industry, governments, consumers and other sectors. The requirements or recommendations contained in published Standards are a consensus of the views of representative interests and also take account of comments received from other sources. They reflect the latest scientific and industry experience. Australian/New Zealand Standards are kept under continuous review after publication and are updated regularly to take account of changing technology.

International Involvement

Standards Australia and Standards New Zealand are responsible for ensuring that the Australian and New Zealand viewpoints are considered in the formulation of international Standards and that the latest international experience is incorporated in national and Joint Standards. This role is vital in assisting local industry to compete in international markets. Both organizations are the national members of ISO (the International Organization for Standardization) and IEC (the International Electrotechnical Commission).

Visit our websites

www.standards.org.au www.standards.govt.nz



GPO Box 476 Sydney NSW 2001
Phone (02) 9237 6000
Email mail@standards.org.au
www.standards.org.au



PO Box 1473 Wellington 6140
Freephone 0800 782 632
Phone (04) 498 5990
Email enquiries@standards.govt.nz
www.standards.govt.nz

This page has been left intentionally blank.