



BSI Standards Publication

Vitreous and porcelain enamels — Regenerative, enamelled and packed panels for air-gas and gas-gas heat exchangers — Specifications

National foreword

This British Standard is the UK implementation of EN ISO 28763:2019. It is identical to [ISO 28763:2019](#). It supersedes [BS EN ISO 28763:2011](#), which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/36, Vitreous enamel coatings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 539 01654 3

ICS 25.220.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2019.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

Vitreous and porcelain enamels — Regenerative, enamelled and packed panels for air-gas and gas-gas heat exchangers — Specifications (ISO 28763:2019)

Émaux vitrifiés — Échangeurs thermiques pour
réchauffeurs air-gaz et gaz-gaz à empilement
de panneaux émaillés remplaçables et
démontables — Spécifications (ISO 28763:2019)

Emails und Emailierungen — Regenerative,
emailierte und gepackte Bleche für Luft-
Gas- und Gas-Gas-Wärmeaustauscher —
Anforderungen (ISO 28763:2019)

This European Standard was approved by CEN on 13 August 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 28763:2019) has been prepared by Technical Committee ISO/TC 107 "Metallic and other inorganic coatings" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2020, and conflicting national standards shall be withdrawn at the latest by March 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 28763:2011.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of [ISO 28763:2019](#) has been approved by CEN as EN ISO 28763:2019 without any modification.

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Steel substrates	2
4.1	Delivery	2
4.2	Analysis	2
4.3	Hydrogen permeability	2
4.4	Fish scaling test	2
4.5	Pickling speed	3
5	Enamel frit	3
5.1	Delivery	3
5.2	Coefficient of expansion	3
5.3	Fusion flow	3
5.4	Boiling-water (vapour phase) resistance	3
5.5	Acid resistance	3
5.6	Thermal-shock resistance	4
5.7	Adherence	4
6	Characteristics of the enamel coating	4
6.1	Adherence	4
6.2	Thickness	4
6.3	Thermal-shock resistance	5
6.4	Fundamental defects	5
6.5	Open defects	5
6.6	Edge covering of gas-gas heaters	6
6.7	Boiling sulfuric acid resistance	6
6.8	Rework	6
7	Characteristics after packing	6
7.1	Packing pressure	6
7.2	Visual examination	6
7.3	Edge covering of gas-gas heaters	7
8	Documentation	7
Annex A (normative) Method for determining thermal-shock resistance of vitreous or porcelain enamel coatings		8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

This second edition cancels and replaces the first edition ([ISO 28763:2008](http://www.iso.org/iso/28763:2008)), which has been technically revised. The main changes compared with previous edition are as follows:

- the normative references have been updated;
- the terms and definitions have been updated;
- references to normative documents and respective clauses have been updated;
- references and requirements for hydrogen permeability of steel have been updated in [Clause 4](#);
- requirements for visual examinations have been amended in [Clause 6](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Vitreous and porcelain enamels — Regenerative, enamelled and packed panels for air-gas and gas-gas heat exchangers — Specifications

1 Scope

This document specifies the minimum requirements and the functional characteristics of enamel coatings applied by any process, such as wet dipping, wet flow-coating, wet spraying, wet electrostatic spraying, wet electrodeposition or dry-powder electrostatic spraying, to profiled steel heat exchanger panels in regenerative heat exchangers, before and after packing in baskets.

For very severe service conditions, or to obtain extended operational life, more stringent limits can be agreed between customer and supplier.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 105-J03](#), *Textiles — Tests for colour fastness — Part J03: Calculation of colour differences*

[ISO 2178](#), *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method*

[ISO 4534](#), *Vitreous and porcelain enamels — Determination of fluidity behaviour — Fusion flow test*

[ISO 7991](#), *Glass — Determination of coefficient of mean linear thermal expansion*

[ISO 8289:2000](#), *Vitreous and porcelain enamels — Low voltage test for detecting and locating defects*

[ISO 19496-1](#), *Vitreous and porcelain enamels — Terminology — Part 1: Terms and definitions*

[ISO 28706-2:2017](#), *Vitreous and porcelain enamels — Determination of resistance to chemical corrosion — Part 2: Determination of resistance to chemical corrosion by boiling acids, boiling neutral liquids, alkaline liquids and/or their vapours*

[ISO 28723](#), *Vitreous and porcelain enamels — Determination of the edge covering on enamelled steel plate to be used in heat exchangers*

[ISO 28764](#), *Vitreous and porcelain enamels — Production of specimens for testing enamels on sheet steel, sheet aluminium and cast iron*

[EN 10204:2004](#), *Metallic products — Types of inspection documents*

[EN 10209:2013](#), *Cold rolled low carbon steel flat products for vitreous enamelling — Technical delivery conditions*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in [ISO 19496-1](#) and the following apply.

thickness of 100 µm to 130 µm. After drying, the coated test sheet shall be fired for 5 min at 820 °C. The test sheet shall then be subjected to thermal treatment at 60 °C to 80 °C for 24 h and subsequently inspected for fish scales. No fish scales are allowed.

4.5 Pickling speed

If required by the enameller, the pickling speed shall be determined in accordance with [EN 10209:2013](#), Annex B, and an acceptable level shall be agreed with the steel manufacturer.

5 Enamel frit

5.1 Delivery

Enamel frit shall be ordered by the enameller with a certificate conforming to the requirements of [EN 10204:2004](#), 3.1, including the results for the items given under [5.5](#) and [5.7](#).

The tests in [5.4](#) and [5.6](#) shall be carried out whenever there is a change in the frit or a change in the milling formula.

When taking delivery of “ready to use” enamel, enamel slip or enamel powder, the enameller may ask for additional requirements for the application properties in the material certificate.

Any other requirements and the test recipes shall be determined by consultation between the enameller (and/or customer) and the frit manufacturer.

5.2 Coefficient of expansion

If required by the enameller, the coefficient of expansion shall be determined in accordance with the house test of the manufacturer of the enamel frit (base material for “ready to use” enamel, enamel slip or powder enamel) or in accordance with [ISO 7991](#).

5.3 Fusion flow

If required by the enameller, the fusion flow shall be determined in accordance with the house test of the manufacturer of the enamel frit (base material for “ready to use” enamel, enamel slip or powder enamel) or in accordance with [ISO 4534](#).

5.4 Boiling-water (vapour phase) resistance

If required by the enameller, the boiling-water (vapour phase) resistance shall be determined in accordance with [ISO 28706-2:2017](#), Clause 14.

When determined in this way, the maximum loss in mass of the enamel coating shall be as given in [Table 1](#).

Table 1 — Maximum loss in mass

Heater type	Mass loss, max.
Air-gas	20 g/m ² /48 h
Gas-gas	6 g/m ² /48 h

5.5 Acid resistance

The boiling sulfuric acid resistance shall be determined in accordance with [ISO 28706-2:2017](#), Clause 11.

5.6 Thermal-shock resistance

If required by the enameller, the thermal-shock resistance shall be determined in accordance with [Annex A](#) at a test temperature of 350 °C on at least three test specimens prepared in accordance with [ISO 28764](#).

After testing five times at the test temperature, the test specimens shall show no damage.

5.7 Adherence

The adherence shall be determined in accordance with [EN 10209:2013](#), Annex C, using test specimens with a known pickling speed (see [4.5](#)) prepared in accordance with [ISO 28764](#).

The method of pre-treatment, application and firing of the enamel shall be described.

6 Characteristics of the enamel coating

6.1 Adherence

Test specimens for the determination of adherence shall be prepared in accordance with [ISO 28764](#) and shall be pre-treated and enamelled under the same conditions as for the production of the heat exchanger panels.

When determined in accordance with [EN 10209:2013](#), Annex C, the adherence of the enamel shall be at least level 2.

Tests shall be carried out on every pre-treated batch of panels.

6.2 Thickness

The thickness shall be determined in accordance with [ISO 2178](#). Adjustment of the measurement equipment shall be carried out on the profile concerned. Select a pair of panels, one corrugated and one undulated, and carry out measurements from point A to point I (see [Figure 1](#)) on the front and reverse faces of each panel. The measurement points shall be situated at least 50 mm from the edge. The measurement points on the corrugated panel shall be as indicated by numbers 1 and 2, and on the undulated panel as indicated by 3. This will result in 54 measurements from each pair of panels tested, 36 from the corrugated panel and 18 from the undulated panel.


The mean of the 54 measurements shall be $150\ \mu\text{m} \pm 30\ \mu\text{m}$, unless a different mean is agreed between customer and supplier at the time of ordering.

Along the area bordering the edges of the panels, the total thickness may measure up to 600 μm (i.e. two faces of 300 μm) plus the thickness of the substrate. If a different mean has been agreed between customer and supplier, the total enamel thickness along the area bordering the edge of the panel may vary, but should preferably be kept to a minimum to avoid chipping and spalling, etc.

With the exception of edges and suspension holes, the application thickness beside the measurement point (such as on both sides of the notches of the corrugation) shall nowhere fall below 80 μm .

Measurements other than those at the points indicated shall be carried out on cross sections using microscopy.

The test shall be carried out on a 2 h cycle.



Key
1, 2 corrugated
3 undulated

Figure 1 — Thickness measurement points

6.3 Thermal-shock resistance

Test specimens for the determination of thermal-shock resistance shall be prepared in accordance with [ISO 28764](#) and shall be pre-treated and enamelled under the same conditions as for the production of the heat exchanger. They shall have an enamel layer thickness of $150\ \mu\text{m} \pm 20\ \mu\text{m}$.

The thermal-shock resistance shall be determined in accordance with [Annex A](#) at a test temperature of $350\ ^\circ\text{C}$ on at least three test specimens.

After testing five times at the test temperature, the test specimens shall show no damage.

The test shall be carried out on every 5 000 kg of enamel frit.

6.4 Fundamental defects

A 100 % visual examination of the enamelled surface shall be carried out for fundamental defects. The enamelled surface shall be free of fundamental defects such as blisters, burn-off, chipping, copperheads, cracking, crazing, fish scaling, spalling and tearing. The enamelled surface shall be visually examined from a minimum distance of 1,5 m and a maximum distance of 2,5 m either in natural light or in D65 artificial daylight in accordance with [ISO 105-J03](#).

NOTE Fire tool marks can be accepted.

6.5 Open defects

Open defects down to the basis metal shall be detected in accordance with [ISO 8289:2000](#), method B.

In a random check of 10 pairs of panels out of a production of 10 000 pairs of panels, the average number of open defects shall be as given in [Table 2](#). This rate of sampling is sufficiently representative of the production whenever the results are within the specified limit. If the results are outside the specified limit, sampling shall be extended to between 2 and 5 per 1 000.

Table 2 — Maximum numbers of open defects

Heater type	Open defects, max.
Air-gas	50/m ²
Gas-gas	15/m ²

Alternatively, if the production process demands it, the number of defects on pairs of heat exchanger panels may be determined by checking 1 % of production on a 2 h cycle.

6.6 Edge covering of gas-gas heaters

If required by the customer, the edge covering of the panels of gas-gas heaters shall be determined in accordance with [ISO 28723](#). The mean shall be agreed between the customer and the supplier at the time of ordering.

6.7 Boiling sulfuric acid resistance

Test specimens for the determination of boiling sulfuric acid resistance shall be prepared in accordance with [ISO 28764](#) and shall be pre-treated and enamelled under the same conditions as for the production of the heat exchanger. They shall have an enamel layer thickness of 150 µm ± 20 µm.

When determined in accordance with [ISO 28706-2:2017](#), Clause 11, the maximum loss in mass of the enamel coating shall be as given in [Table 3](#).

The test shall be carried out on every 5 000 kg of enamel frit.

Table 3 — Maximum loss in mass

Heater type	Mass loss, max.
Air-gas	10,0 g/m ² /18 h
Gas-gas	2,0 g/m ² /18 h

6.8 Rework

In the event of enamelled elements being rejected, a maximum of 5 % of rework shall be accepted.

7 Characteristics after packing

7.1 Packing pressure

The packing pressure applied to the corrugated and undulated plates shall be ± 1 000 kg/m², preferably in the upper limit of the range 4 000 kg/m² to 8 000 kg/m². The surface area, in m², of each filled basket is determined from the length and width of the middle pair of plates in the load.

7.2 Visual examination

For gas-gas heaters, a visual examination shall be carried out for defects such as chipping, cracking or spalling. Special attention shall be given to the contact points between the corrugated and undulated plates (the second, the middle and the last but one pair of panels in the basket). The maximum number of defects/m² at the contact points shall be agreed between the customer and the supplier.

The visual examination shall be performed after pressurizing the basket, complete with elements, but without the pack being welded.

The visual examination shall be carried out on 2 % of the elements and a minimum of one basket per rotor shall be tested.

7.3 Edge covering of gas-gas heaters

If required by the customer, the edge covering of gas-gas heater panels shall be determined in accordance with [ISO 28723](#) or by visual examination of the edges in the flow direction.

The edge-covering test shall be performed after pressurizing the basket, complete with elements, but without the pack being welded.

8 Documentation

If required by the customer, the enameller shall provide the test results for the measurements listed in [Table 4](#), together with full details of the process parameters.

Table 4 — Summary of required tests

Test	Subclause	Gas-gas heaters	Air-gas heaters
Steel (Clause 4)			
Certificate: EN 10204:2004 , 3.1	4.1	Required	Required
Analyses	4.2	Required	Required
Hydrogen permeability or fish scaling test	4.3 4.4	Required	Required
Pickling speed	4.5	If required	If required
Frit (Clause 5)			
Certificate: EN 10204:2004 , 3.1	5.1	Required	Required
Coefficient of expansion	5.2	If required	If required
Fusion flow	5.3	If required	If required
Water vapour resistance	5.4	If required	If required
Acid resistance	5.5	Required	Required
Thermal shock	5.6	If required	If required
Adherence	5.7	Required	Required
Enamel coating (Clause 6)			
Adherence	6.1	Required	Required
Thickness	6.2	Required	Required
Thermal shock	6.3	Required	Required
Fundamental defects	6.4	Required	Required
Open defects	6.5	Required	Required
Edge covering	6.6	If required	Not applicable
Acid resistance	6.7	Required	Required
Rework	6.8	Required	Required
After packing (Clause 7)			
Packing pressure	7.1	Required	Required
Visual examination	7.2	Required	Not applicable
Edge covering	7.3	If required	Not applicable
Documentation (Clause 8)		If required	If required

Annex A (normative)

Method for determining thermal-shock resistance of vitreous or porcelain enamel coatings

A.1 Procedure

Heat the test specimens in a forced-air-convection oven to the required test temperature and hold at that temperature for 10 min.

Remove each test specimen from the heat source and, within 5 s, plunge it into water at a temperature of 15 °C to 20 °C and completely immerse it for at least 30 s.

Remove the test specimen from the water, dry and allow to cool to ambient temperature.

Repeat the procedure four times so that five thermal cycles are completed.

A.2 Evaluation

Inspect the test specimens for any visible sign of damage, such as chipping, cracking, crazing or spalling.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

